

STONE



1" STONE

INFORMATION

ARTAIC INNOVATIVE MOSAIC

SELECTION


1" x 1" x 3/8" 39 Colors

All colors available in Polished, Tumbled & Honed finishes

APPLICATIONS:

Residential/Commercial Indoor/Outdoor Wall/Flooring









Artaic Name Artaic Inventory ID					1" Polished/Honed Stone A-1-ST-P&H200+	1" Tumbled Stone A-1-ST-T200+
ASTM	NOTES: All values vary a	cross different types of	stone All Artaic stone no	asses ASTM standards for	commercial floor use	
ASTM C-97: Density			2 (2.59) for structural use		162.3 - 193.5 (2.60 - 3.095)	162.3 - 193.5 (2.60 - 3.095)
ASTM C-97: Water Absorption	Impervious	Vitreous	Semi-Vitreous	Non-Vitreous		
·	≤ 0.5%	0.5-3%	3-7%	7-20%	= 0.3% - Impervious</td <td><!--= 0.3% - Impervious</td--></td>	= 0.3% - Impervious</td
ASTM C-99: Modules of Rapture		Min psi (MPa) = 1000	(6.89) for structural use.	•	2235.12 - 4136.43 (15.4-28.5)	2235.12 - 4136.43 (15.4-28.5
ASTM C170: Compression Strength		Min psi (MPa) = 7500	(52) for structural use.		10,570 - 33,011 (72.9-227.6)	10,570 - 33,011 (72.9-227.6)
ASTM C-241: Abrasion Resistance		Min Hardness = 1	0 for structural use.		18 - 25	18 - 25
ASTM C-424: Crazing Resistance		One cycle	ass-or-fail test		Pass	Pass
ASTM C-880: Flexural Strength		Min psi (MPa) = 1000	(6.89) for structural use.		1117.56 - 5413.64 (7.7 - 37.3)	1117.56 - 5413.64 (7.7 - 37.3)
ASTM C-499: Facial & Thickness Dimensions	Nomin	al Size	Vo	alue	0.94" x 0.94"	0.9375" x 0.9375"
	Caliber	Range	Value		Range: 0.027"	Range: 0.027"
	Thick	ness	Value		0.375"	0.315"
Artaic Production SQFT: Dimensions	Nominal Si	ze - Inches	Value		11.96875" x 11.96875"	11.9375" x 11.9375"
Artaic Production SQFT: Dimensions	Tile C	ount	Value		12 x 12	12 x 12
Artaic Production SQFT: Tiles / SQFT	Tile C	ount .	Value		144	144
Artaic Production SQFT: Weight (no grout)	LE	S	Value		4.5	4.25
Artaic Production SQFT: Weight (with grout)	LE	S	Value		5	4.75
Artaic Production SQFT: Grout Width	Nominal Si	ze - Inches	Value		0.0625	0.063
ASTM C-1028: Static Coefficient of Friction	C.0	D.F.	Resulting Classification			
	0 ≤ to	≤ 0.39	Hazardous - Excessive: No floor use			
		0.40 ≤ to ≤ 0.59 Satisfactory: Low to regular traffic residential use			Wet: 61 - Satisfactory	
	0.60 ≤ to		Satisfactory: Light traffic commercial use		Dry: 81 - Excellent	Dry: 81 - Excellent
		≥ 0.80 Excellent: All uses				
ASTM C-1378: Staining Resistance	ing Resistance Resistance Class		Max. # of samples that retain a stain			
		A	0		Pass - Class A	Pass - Class A
	E	3	1			
		3	2			
)	3			
	E	E		more		

SEALANTS	NOTES: Honed and tumbled stone needs to be sealed to prevent staining. Sealants have a negligible impact on metrics above.
Scenario 1 - Normal Sealing	For walls, backsplashes, etc, use a simple "Grout & Tile Sealer" solution available from several brands at many hardware stores
	For walls, backsplashes, etc, where a slight ehancement/darkening of the stone's natural color is desired, use a "Stone Enhancer & Sealer" available from several brands at many hardware stores.
Scenario 3 - Sealing for Floor Use	For high traffic floor applications, use a "Penetrating Stone, Grout & Tile Sealer" available from several brands at many hardware stores.

9/16" STONE

INFORMATION


SELECTION

9/16" x 9/16" x 3/8" 39 Colors All colors available in Polished, Tumbled & Honed finishes






Residential/Commercial Indoor/Outdoor Wall/Flooring









ASTM C-97: Density		Min lb/ft3 (g/cm3) = 162 (2.59) for structural use.				162.3 - 193.5 (2.60 - 3.095)
ASTM C-97: Water Absorption	Impervious	Vitreous	Semi-Vitreous	Non-Vitreous	162.3 - 193.5 (2.60 - 3.095)	, , , , , , , , , , , , , , , , , , , ,
	≤ 0.5%	0.5-3%	3-7%	7-20%	= 0.3% - Impervious</td <td><!--= 0.3% - Impervious</td--></td>	= 0.3% - Impervious</td
ASTM C-99: Modules of Rapture		Min psi (MPa) = 1000	00 (6.89) for structural use.		2235.12 - 4136.43 (15.4-28.5)	2235.12 - 4136.43 (15.4-28.5)
ASTM C170: Compression Strength		Min psi (MPa) = 7500 (52) for structural use.			10,570 - 33,011 (72.9-227.6)	10,570 - 33,011 (72.9-227.6)
ASTM C-241: Abrasion Resistance		Min Hardness = 1	0 for structural use.		18 - 25	18 - 25
ASTM C-424: Crazing Resistance		One cycle p	oass-or-fail test		Pass	Pass
ASTM C-880: Flexural Strength		, ,			1117.56 - 5413.64 (7.7 - 37.3)	1117.56 - 5413.64 (7.7 - 37.3)
ASTM C-499: Facial & Thickness Dimensions	Nomir	Nominal Size		Value		0.60" x 0.60"
	Calibe	Caliber Range		Value		Range: 0.027"
	Thic	rness	Value		0.375"	0.315"
Artaic Production SQFT: Dimensions	Nominal S	ze - Inches	Value		11.96875" x 11.96875"	11.9375" x 11.9375"
Artaic Production SQFT: Dimensions	Tile (Count	Value		18 x 18	18 x 18
Artaic Production SQFT: Tiles / SQFT	Tile (Count	Value		324	324
Artaic Production SQFT: Weight (no grout)	L	3S	Value		4.05	3.85
Artaic Production SQFT: Weight (with grout)	L	3S	Value		4.55	4.33
Artaic Production SQFT: Grout Width	Nominal S	ze - Inches	Value		0.0625	0.063
ASTM C-1028: Static Coefficient of Friction	C.	C.O.F.		Resulting Classification		
	0 ≤ to	0 ≤ to ≤ 0.39		Hazardous - Excessive: No floor use		
	0.40 ≤ t	0.40 ≤ to ≤ 0.59		Satisfactory: Low to regular traffic residential use		Wet: 61 - Satisfactory
	0.60 ≤ t	0.60 ≤ to ≤ 0.79		Satisfactory: Light traffic commercial use		Dry: 81 - Excellent
	≥(≥ 0.80		Excellent: All uses		
ASTM C-1378: Staining Resistance	Resistan	Resistance Class		Max. # of samples that retain a stain		
-		A		0		Pass - Class A
		В		1		
		2	2			
)	3			
				4 or more		

SEALANTS	NOTES: Honed and tumbled stone needs to be sealed to prevent staining. Sealants have a negligible impact on metrics above.		
Scenario 1 - Normal Sealing	For walls, backsplashes, etc, use a simple "Grout & Tile Sealer" solution available from several brands at many hardware stores		
	For walls, backsplashes, etc, where a slight ehancement/darkening of the stone's natural color is desired, use a "Stone Enhancer & Sealer" available from several brands at many hardware stores.		
Scenario 3 - Sealing for Floor Use	For high traffic floor applications, use a "Penetrating Stone, Grout & Tile Sealer" available from several brands at many hardware stores.		

3/8" STONE

INFORMATION


SELECTION

3/8" x 3/8" x 3/8" 39 Colors All colors available in Polished, Tumbled & Honed finishes



APPLICATIONS:

Residential/Commercial Indoor/Outdoor Wall/Flooring











Artaic Name					3/8" Polished/Honed Stone	3/8" Tumbled Stone
Artaic Inventory ID						
ASTM	NOTES: All values vary a	cross different types of	stone. All Artaic stone po	asses ASTM standards for	commercial floor use.	
ASTM C-97: Density			2 (2.59) for structural use		162.3 - 193.5 (2.60 - 3.095)	162.3 - 193.5 (2.60 - 3.095)
ASTM C-97: Water Absorption	Impervious	Vitreous	Semi-Vitreous	Non-Vitreous	,	,
	≤ 0.5%	0.5-3%	3-7%	7-20%	= 0.3% - Impervious</td <td><!--= 0.3% - Impervious</td--></td>	= 0.3% - Impervious</td
ASTM C-99: Modules of Rapture		Min psi (MPa) = 1000	(6.89) for structural use.	•	2235.12 - 4136.43 (15.4-28.5)	2235.12 - 4136.43 (15.4-28.5
ASTM C170: Compression Strength		Min psi (MPa) = 7500	(52) for structural use.		10,570 - 33,011 (72.9-227.6)	10,570 - 33,011 (72.9-227.6)
ASTM C-241: Abrasion Resistance		Min Hardness = 10 for structural use.			18 - 25	18 - 25
ASTM C-424: Crazing Resistance		One cycle i	oass-or-fail test		Pass	Pass
ASTM C-880: Flexural Strength		Min psi (MPa) = 1000	(6.89) for structural use.		1117.56 - 5413.64 (7.7 - 37.3)	1117.56 - 5413.64 (7.7 - 37.3
ASTM C-499: Facial & Thickness Dimensions	acial & Thickness Dimensions Nominal Size Value		alue	0.375" x 0.375"	0.374" x 0.374"	
	Caliber	Range	Value		Range: 0.027"	Range: 0.027"
	Thick	iness	Value		0.375"	0.315"
Artaic Production SQFT: Dimensions	Nominal Si	ze - Inches	Value		11.7261" x 11.7261"	11.7934" x 11.7934"
Artaic Production SQFT: Dimensions	Tile C	ount	Value		27 x 27	27 x 27
Artaic Production SQFT: Tiles / SQFT	Tile C	ount	Value		712	712
Artaic Production SQFT: Weight (no grout)	LE	3S	Value		3.98	3.98
Artaic Production SQFT: Weight (with grout)	LE	3S	Value		4.48	4.33
Artaic Production SQFT: Grout Width	Nominal Si	ze - Inches	Value		0.0625	0.063
ASTM C-1028: Static Coefficient of Friction	C.C	D.F.	Resulting Classification			
	0 ≤ to	≤ 0.39	Hazardous - Excessive: No floor use			
	0.40 ≤ to		Satisfactory: Low to regular traffic residential use			Wet: 61 - Satisfactory
	0.60 ≤ to		Satisfactory: Light traffic commercial use		Dry: 81 - Excellent	Dry: 81 - Excellent
	≥0		Excellent: All uses			
ASTM C-1378: Staining Resistance	Resistan	ce Class	Max. # of samples that retain a stain			
	/	A	0		Pass - Class A	Pass - Class A
	E	3	1			
			2			
)	3			
	E	E 4 or more		more		

SEALANTS	NOTES: Honed and tumbled stone needs to be sealed to prevent staining. Sealants have a negligible impact on metrics above.		
Scenario 1 - Normal Sealing	For walls, backsplashes, etc., use a simple "Grout & Tile Sealer" solution available from several brands at many hardware stores		
	For walls, backsplashes, etc, where a slight ehancement/darkening of the stone's natural color is desired, use a "Stone Enhancer & Sealer" available from several brands at many hardware stores.		
Scenario 3 - Sealing for Floor Use	For high traffic floor applications, use a "Penetrating Stone, Grout & Tile Sealer" available from several brands at many hardware stores.		



3/8", 9/16", 1" STONE





*Colors are subject to change, shade variations may occur.



3/8", 9/16", 1" STONE













